

TABLE 1 Grading Requirements

Sieve Size	Amounts Finer than Each Laboratory Sieve (Square Openings), weight %				
	CONCRETE		Fine Aggregate		Coarse Aggregate
	Size No. 1	Natural	Manufactured	Size No. 8	Size No. 80
3/4-in. (19.0-mm)	100	100	100	100	100
No. 4 (4.75-mm)	95 to 100	100	100	85 to 100	90 to 100
No. 8 (2.36-mm)	80 to 100	95 to 100	100	10 to 30	20 to 55
No. 16 (1.18-mm)	50 to 85	70 to 100	70 to 100	0 to 10	5 to 30
No. 30 (600- μ m)	25 to 80	40 to 75	40 to 75	0 to 5	0 to 10
No. 50 (300- μ m)	10 to 30	10 to 35	20 to 40	...	0 to 5
No. 100 (150- μ m)	2 to 10	2 to 15	10 to 25
No. 200 (75- μ m)	0 to 10

8. Methods of Sampling and Testing

8.1 Sample and test the aggregate in accordance with the following standards, except as otherwise provided in this specification:

8.1.1 Sampling—Practice D 75.

8.1.2 Grading—Method C 136.

8.1.3 Amount of Material Finer Than No. 200 (75- μ m) Sieve—Test Method C 117.

8.1.4 Organic Impurities—Test Method C 40.

8.1.5 Effect of Organic Impurities on Strength—Test Method C 87.

8.1.6 Friable Particles—Test Method C 142.

8.1.7 Lightweight Constituents—Test Method C 123.

8.1.8 Soundness—Test Method C 88.

8.1.9 Density—Determine the density of the fine aggregate in accordance with Test Method C 128. Use the bulk specific gravity (saturated surface dry-SSD) determined in the calculation of the air content of the mortars, as required by Specification C 270.

9. Keywords

9.1 aggregate; coarse aggregate; fine aggregate; grout; masonry; sand; soundness

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either approved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 1919 Race St., Philadelphia, PA 19103.